



Flexiphalt® 340A

Flexiphalt 340A is a premium grade, fully networked SBS modified bitumen. It is specifically designed for use in hot mix asphalt and is an ideal choice for improving the performance of pavements carrying heavy vehicles or very high traffic volumes.

The use of Flexiphalt 340A provides the following performance advantages:

- Good resistance to raveling
- Outstanding resistance to deformation
- Excellent resistance to cracking
- AASHTO M332 specification grade PG64V-22.

WHERE TO USE

- Asphalt pavements subjected to slow moving, heavy axle loads
- Asphalt pavements subjected to traffic flows >20 million ESAL
- Pavements experiencing cracking.
- SMA and porous asphalt where improved binder properties, increased binder film thicknesses and minimal binder drainage are required.

APPLICATION AND DESIGN

- The asphalt design procedure and bitumen content is identical to that used for unmodified asphalt. The following guidelines may assist in obtaining adequate compaction:
- The recommended temperature range for asphalt production using Flexiphalt 340A is 165–180°C.
- The mix and compaction temperatures for Austroads, SP-2 and MS-2 mix design purposes are 175°C and 160°C respectively.
- Ensure that the rollers are of sufficient size and quantity.
- Establish an appropriate rolling pattern.
- Avoids delays and begin compaction immediately. Compaction is best achieved before the temperature falls below 110°C.
- Consult the manufacturer if further guidance is required.
- A Safety Data Sheet (SDS) is available upon request.



Typical Properties of Flexiphalt 340A

Title	Method	Property
Viscosity (135°C)	ASTM D4402	1.4 Pa.s
G*/sin = 1.00 kPa	ASTM D7175	74°C
Jnr (3200 Pa, 64°C)	ASTM D7405	0.6 kPa ⁻¹
Elastic Recovery (64°C)	ASTM D7405	40%
Density (25°C)	ASTM D70	1.02 kg/L

For more information please contact:

Higgins Bitumen, 26 Waitangi Road,
PO Box 421, Napier. E: HBM@higgins.co.nz

To the best of our knowledge the information contained in this document is correct. Since the products described herein are being continuously improved, the specified properties may vary as improvements are made to production processes and product quality. This document may be revised at any time.