

Higgins CSS-1 is a versatile cationic slow set emulsion that finds a wide range of applications in pavement construction.

It is an over-stabilised emulsion that can be used to manufacture solvent-less cold mixes, suppress dust or stabilise granular pavement layers. CSS-1 can be diluted with potable water for specialist applications.

### > WHERE TO USE

- Tack coat
- Aggregate Precoating
- Enrichment and Fog Seals
- Slurry Sealing
- Dense Graded Cold Mix
- Cold In-Place Recycling and Stabilisation
- Dust Suppression.

### > TYPICAL PROPERTIES OF CSS-1

Residual Binder Type		Penetration Grade
Binder Content	In-House Method NTM 02	60%
Brookfield Viscosity (25°C)	ASTM 2196	100 mPa.s
Sieve Residue (150µm)	AS2341.26	0.1%

### > APPLICATION AND DESIGN

Storage Life	Up to 60 Days
Storage Temperature	10 - 50°C
Application Temperature	20 - 40°C
Air and Pavement Temperature	10°C and rising

- Higgins CSS-1 can be diluted with potable water. Once diluted, it should be used that day as settlement of the emulsion will rapidly occur
- Consult the manufacturer if further guidance is required
- A Safety Data Sheet (SDS) is available upon request.

For more information on the availability of CSS-1 please contact:

Higgins Bitumen (a division of Higgins Contractors Ltd),  
PO Box 421, Napier  
P: (06) 834-1589 E: HBM@higgins.co.nz

October 2014  
Version 3

To the best of our knowledge the information contained in this document is correct. Since the products described herein are being continuously improved, the specified properties may vary as improvements are made to production processes and product quality. This document may be revised at any time.